



PRODUCT DATA SHEET TUFF-TAPE™

3 pages

DESCRIPTION:

Canadian Construction Products Tuff-Tape™ is a prefabricated peel and stick laminate consisting of a top sanded asphalt membrane layer, and an adhesive layer of modified rubber bituminous compound reinforced with a high strength composite woven fibreglass and non-woven polyester fabric backed by a clear silicone release sheet.

PURPOSE:

Canadian Construction Products Tuff-Tape™ is a dual purpose membrane designed to retard reflective cracking between existing road surfaces and paving overlays and to help waterproof to eliminate moisture intrusion to the crack. When used as a reflective cracking membrane it bonds to the existing paved surface, waterproofing and inhibiting cracks reflecting into new paving overlays. When used as a waterproofing membrane it eliminates water infiltration to culverts, backwalls and various vertical surfaces.

WHERE TO USE IT:

As a reflective cracking membrane Canadian Construction Products Tuff-Tape™ is particularly effective when used to inhibit reflective cracking in the longitudinal direction where the dividing line between adjacent road sections at the center, or at the edges, has increased in width. It is equally effective where cracking is in the transverse direction or of irregular occurrence.

As a waterproofing membrane Canadian Construction Products Tuff-Tape™ forms an impenetrable moisture barrier when used to waterproof block, concrete, asphalt, brick or wood. Not recommended for use as a Bridge Deck Waterproofing Membrane.

HOW TO USE IT:

Surface Preparation: Surfaces should be dry and free from dust, dirt, mud, oil, grease and other contaminants. Holes and voids should be patched with a suitable material. Level course asphalt pavement potholes prior to placement of membrane.

Use of Adhesive:

Canadian Construction Products special adhesive primer (or equivalent) is required. Adhesive should be applied at approximately 0.2 litres per sq.m. for road reinforcement applications and minimum 0.3 litres per sq.m. for waterproofing and load bearing applications.



CANADIAN CONSTRUCTION PRODUCTS

#4 19747 TELEGRAPH TRAIL
LANGLEY, BC, CANADA V1M 3E6
TEL: (604) 888-7818 FAX: (604) 888-8191

Application of Tuff-Tape™ Membrane when used as a reflective cracking system:

The membrane should be unrolled and the release sheet removed. The membrane should be positioned and pressed into positive contact with the dry substrate. Roll ends should be overlapped four 100mm. Apply adhesive as required. Vehicle tire pressure will provide additional insurance of maximum adhesion. However, for most paving applications the membrane can be pressed with foot traffic, hand rollers or machine rollers. Extend membrane 150mm past cracks.

Application of Tuff-Tape™ Membrane when used as a waterproofing system:

An application of adhesive to all surfaces receiving membrane is required. Adhesive should be stirred prior to use and applied by brush, squeegee or roller, or spray. Avoid excessive build-up of adhesive and allow to dry completely prior to the application of the membrane. Dry times will vary depending on air temperature, airflow and humidity, with the average time being 30-90 minutes.

Tuff-Tape™ Waterproofing Membrane is applied to vertical surfaces by using precut sections of membrane and running the membrane from top to bottom. The release film is removed as membrane is pressed into place. Subsequent membrane sheets are overlapped a minimum 75mm.

Horizontal applications are accomplished using the same method with membrane running from the low point in a shingle effect to the high point of the surface being waterproofed.

PHYSICAL PROPERTIES:

PROPERTY	TEST METHOD	VALUE
Thickness		3.0 mm +/- 0.2mm
Strain	CAN/CGSB 37.56-M 9 th draft	795 kg / m (MD)
Breaking	CAN/CGSB 37.56-M 9 th draft	1,530 kg / m (MD)
Elongation Percent	CAN/CGSB 37.56-M 9 th draft	60 (MD)
Puncture Resistance	CAN/CGSB 37.56-M 9 th draft	57 kg
Pliability	CAN/CGSB 37.56-M 9 th draft	-30°C, -30°C after 90 days
Tear Resistance	CAN/CGSB 37.56-M 9 th draft	13 kg

TEST DATA: N/A



CANADIAN CONSTRUCTION PRODUCTS

#4 19747 TELEGRAPH TRAIL
LANGLEY, BC, CANADA V1M 3E6
TEL: (604) 888-7818 FAX: (604) 888-8191

STORAGE

Store upright only. Prior to use keep membrane temp at 15 to 25 C. Keep material dry before placement and paving. Keep membrane below 35 C for placement.

ORDERING INFORMATION:

Canadian Construction Products Tuff-Tape™ comes standard in 10 meter rolls at 1 meter wide weighing 33 kg. Other widths are also available upon request.

If you have any questions, call Canadian Construction Products at 604-888-7171.

The technical data furnished is true and accurate to the best of our knowledge. However, no guarantee of accuracy is given or implied. We guarantee our products to conform to our quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products determined to be defective by our Quality Control standards, exclusive of labour for installation and/or subsequent damage resulting/causing functional damage either directly or indirectly. Prompt reporting (within four (4) working days) of suspected defective product is required. Prices and cost data shown are subject to change without prior notice.

Updated: July 4, 2011