

METAZEAL® AJ

METAZEAL® AJ is our original pre-formed closed-cell low-density foam material that can be used as a joint sealer/filler in our CEVA expansion joint systems or as a gasket.

E®-POXY

**Pre-Formed Expansion Joints
CSI Section 05800 & 07915**

PRODUCT DESCRIPTION

Metazeal AJ is a gray colored pre-formed closed-cell low-density foam joint seal. The material is typically used as an expansion joint seal or as a gasket in bridge, commercial building, parking, water treatment facility, and industrial applications. Metazeal AJ. When installed in our Ceva Joint Systems, the material acts as a water tight seismic expansion joint seal.

Additional features include the ability of the material to be installed in applications with standing water or once installed (bonding agent cured) to withstand hydrostatic pressure. Metazeal AJ is typically recessed 1/8" (3mm) below the surface of the joint opening. As the material is relatively flush to the surface, it is self-cleaning and rejects debris. Metazeal AJ material is safe for use in potable and processed water applications.

Metazeal AJ meets ADA criteria for ground and floor surfaces as stated in the rules and regulations section of the Federal Register Volume 58 no.144, US Access Board.

| FEATURES | BENEFITS |
|---|--|
| Dynamic movement range of -60%, +30% & ±60% shear | Seismic expansion joint seal |
| Withstand up to 70 ft.. of head pressure | Can be used in below grade applications |
| Ease of installation | Labor savings |
| Chemically Resistant | Excellent for use in water treatment and other industrial applications |
| Field directional changes & heat welds | Ideal for stage construction or segmental repairs. |
| Closed cell | 100% water tight |

USES:

Applications

- Expansion joints
- Seismic joints
- Gaskets
- Seismic retrofit
- Cast-in-place joints

Locations

- Bridges/Highways/Tunnels/Airport Runways
- Commercial Buildings
- Water Treatment Facilities
- Tanks / Pools
- Parking Garages
- Industrial Facilities

Substrates

- Concrete
- Elastomeric concrete
- Steel
- Wood
- Most construction materials

WARRANTY

Manufacturer WARRANTS that the product conforms to its chemical description and is reasonably fit for the purpose stated on its Technical Bulletin when used in accordance with its directions. Manufacturer makes NO OTHER WARRANTY either expressed or implied. Buyer assumes all risk in handling. For further Technical or Application Information, contact Chase Construction Products

Updated 09/19/08
S002 Rev 07/30/07

| PHYSICAL REQUIREMENTS | | |
|---|------------------------|---|
| Test | Test Method | Result |
| Compression Set | ASTM D3575 Suffix B | 50% Compression 2hr Recovery 10% Set 24hr Recovery 9% Set |
| Extrusion | ASTM D545 | .25" (6.4mm) max |
| Elongation | ASTM D3575 Suffix T | 185% - 275% |
| Density | ASTM D3575 Suffix W | 2.7 - 3.4 lbs/ft ³ |
| Water Absorption | ASTM 3575 Suffix L | .035 lbs/ft ² avg. |
| Tensile | ASTM D3575 Suffix T | 92 - 140 psi (640 - 950 KPa) |
| Recovery | ASTM D545 | 98.9% |
| Tear Resistance | ASTM D624 | 10-20 lbs/in (1.79 - 3.57 kg/cm) |
| Compression Deflection | ASTM D3575 | 25% 6 psi avg. 50% 16 psi avg. |
| Meets ASTM 1056 Type 2, Class B, Grade 2 & AASHTO T-42-84 Modified | | |

MOVEMENT CAPABILITY

Metazeal AJ is capable of working in 60% compression and 30% tension when used in our Ceva Expansion Joint Systems with the appropriate Eva-Pox Bonding Agent. Metazeal AJ can handle up to 60% ± total horizontal or vertical shear movement.

SIZING GUIDELINES

Metazeal AJ is typically sized at a minimum of 25% larger than the joint opening but can vary from a minimum of 10%. The amount of compression will vary due to seasonality, temperature and designed movement of the joint. Please see our sizing chart and contact your sales representative for appropriate sizing for your application.

ENGINEERED SURFACE PREPARATION

When bonded in place with an Eva-Pox Bonding Agent, the Joint Material shall have E.S.P. (Engineered Surface Preparation) grooves along the bond surfaces at a distance of no less than 1/4" and no more than 1/2" apart (6mm - 13mm). The grooves are approximately 1/8" deep x 1/8" (3mm x 3mm) wide and run the entire length of the joint, increasing the bond surface for enhanced bond performance.

PERFORMANCE INSTALLATION ENHANCEMENT

On joint material exceeding 3 inches in width and depth, Performance Installation Enhancement or P.I.E. is recommended. When P.I.E. is added to the joint material, an additional inch of depth is added for beveling. This bevel creates a natural trapezoidal shaped product that is easier to install.



Distributed By:
CANADIAN CONSTRUCTION PRODUCTS®
PH: 604-888-7171
www.ccpccanada.com
sales@ccpcanada.com

METAZEAL® AJ**E®-POXY****Pre-Formed Expansion Joints
CSI Section 05800 & 07915****JOINT MATERIAL LIMITATIONS**

Directional Changes: All directional changes in Joint Material must be done using the heat welding method. This is done by placing the Joint Material ends against a Teflon coated heating iron at 350°F (176°C) for 10 - 20 seconds. The ends are then placed together tightly and fusion bonded. Heat welds are not required for turns. For vertical turns, the maximum angle the joint material can sustain without heat welding is 115°. For horizontal turns, the maximum angle the joint material can sustain without heat welding is 135°. Heat welds will add to the aesthetics of an installation and are required for horizontal 90° turns.

Joint Variations: If a joint opening is not uniform, please contact your sales representative.

Skews: Metazeal AJ does not have skew limitations. Please be aware that the working limitations of 50%± shear, 50% compression and 25% tension for the joint material must be adhered to.

Operational Temperature Range: The physical and chemical properties of the Joint Material do not alter significantly within the recommended temperature range of -94°F to 160°F (-70°C to 71°C).

Maximum Joint Opening: When the expansion joint is subjected to pedestrian or vehicular traffic, the following limitations apply:

Vehicular Traffic: Maximum Joint Opening of 4" with out a cover plate.

Pedestrian Traffic: Maximum Joint Opening of 4" with out a cover plate

Storage: Joint material shall be stored in an area that maintains a temperature between 50°F (10°C) and 90°F (32°C).

PLEASE BE AWARE THAT STORAGE CONTAINERS ARE NOT ACCEPTABLE MEANS OF STORAGE IF THEY EXCEED 90°F (32°C).

MANUFACTURING TOLERANCES:

The preformed Joint Material shall be the thickness and width described in the contract or on the plans within a depth tolerance of +10% to -5% and a width tolerance of +2% to -2%.

PACKAGING:

Metazeal AJ is custom fabricated to your specific order. Material can be fabricated to any width at a minimum of 1/2". Maximum depth of the material is 6". Typical lead time for custom fabricated orders is 3-10 business days. Lead time will vary due to order size and volume.

Also available in sheets:

- 1" x 38" x 78"
- 2" x 38" x 78"
- 3" x 38" x 78"
- 4" x 38" x 78"
- 5" x 38" x 78"
- 6" x 38" x 78"

MANUFACTURER'S CERTIFICATIONS:

"Manufacturer's Certifications" are available on material.

"Manufacturer Representatives" are available for on site representation if requested; the representative will certify materials and proper installation procedures. This is required by the manufacturer in order to qualify for any warranty either expressed or implied. Please contact your sales representative for details and applicable costs.

WARRANTY

Manufacturer WARRANTS that the product conforms to its chemical description and is reasonably fit for the purpose stated on its Technical Bulletin when used in accordance with its directions. Manufacturer makes NO OTHER WARRANTY either expressed or implied. Buyer assumes all risk in handling. For further Technical or Application Information, contact Chase Construction Products

Updated 09/19/08
S002 Rev 07/30/07

INSTALLATION PROCEDURES:**Surface Preparation:**

Brush blast all concrete surfaces in direct contact with joint seal. Concrete surfaces should be free of all contaminants and latent build up. Blow dirt or debris from the joint openings and joint surfaces with oil free compressed air. Steel surfaces must be cleaned to SSPC 10 or better. Ensure that all moisture is removed from steel surfaces prior to applying the bonding agent. Use of a propane wand is acceptable.

Seal Installation:

The manufacturers published installation procedures shall be followed at all times. Mask the areas adjacent to the joint opening. One suggestion is to use approximately 12" (300mm) of plastic sheeting and tape along edges to keep the surrounding areas clean. Be sure that the tape does not actually go into the joint opening but back approximately 1/8" (3mm) from the joint edge. Lay out joint material next to its joint opening to check for appropriate length and width. Joint should be sized 25% larger than joint opening at near neutral but never less than 10% oversized or greater than 35% oversized. Heat welds and other directional changes should be cut and made. All welds should be allowed to cool 15 minutes before mixing the adhesive.

Begin mixing the epoxy adhesive following the manufacturer's specified mixing procedures and start at one end or at an intersection or corner. Apply the epoxy adhesive to both sides of the concrete substrate surfaces.

Apply enough adhesive to coat the substrate to an approximate thickness of 40mils (1mm). Apply the epoxy bonder on both surfaces working it in the direction ahead of the joint material, not more than 20' (6m) ahead.

Apply the epoxy adhesive to both sides of the joint material. Apply enough to coat and fill the grooves on the joint material, approximately 40mils (1mm) thick. Install the coated material at the curb, intersection, or corner, where the epoxy was initially applied on the substrate.

The joint material should be installed 1/8" (3mm) below the joint edge and should not protrude above the joint edge.

Continue in the same direction as the epoxy was initially applied. DO NOT push at an angle or pull the material, as this will stretch the material and is unacceptable.

Clean the epoxy left on the surface of the material as soon as it is pushed into the desired depth. DO NOT allow the epoxy to cure before removing it. Use a clean trowel or a putty knife tilted at an angle opposite the direction of movement. DO NOT allow any epoxy bonder near any area to be cut and welded until the weld is completed otherwise the weld will not hold. Once the joint is installed and cleaned, remove the tape from the joint edges before the epoxy cures.

Allow the bonder to set, approximately 20 minutes, at 77°F (25°C), before traffic is allowed onto the joint. Slightly longer time is required during cooler weather.

When a continuous joint cannot be finished, the epoxy bonder on the substrate and also on the joint material must end evenly. Install the joint past the epoxied surfaces at least 6 to 12 inches (150 - 300mm) dry, or without epoxy. This can be pulled out later to be re-welded and the installation continued.



Distributed By:
CANADIAN CONSTRUCTION PRODUCTS
PH: 604-888-7171
www.ccpCanada.com

sales@ccpCanada.com